

UNICOAT SKIMCOAT (Smooth/Coarse)

UNICOAT STUCCO SYSTEMS



PRODUCT DATA SHEET

PRODUCT DESCRIPTION

UNICOAT SKIMCOAT is a pre-blended dry mixture of cement, sand, and cement modifiers, to create a smooth or coarse durable texture mix for skimming and texturing over existing stucco base coats, masonry, concrete surfaces.

UNICOAT SKIMCOAT is available in two forms designated as Texture Mix Smooth and Texture Mix Coarse.

UNICOAT SKIMCOAT can be modified with our **Unicoat Admixture 2000** to increase crack resistance, flexural strength and speed the curing process.

UNICOAT SKIMCOAT SMOOTH is designed to be applied by hand to achieve a smooth slick look or a very fine skip trowel hand texture.

UNICOAT SKIMCOAT COARSE can create a sand float texture finish or a heavy Spanish lace texture finish. Both products can be sprayed on and applied to create different splatter and dash textures as well.

UNICOAT SKIMCOAT can also be used to repair and level a one-coat or 3-coat plastered wall as well.

APPROVED SUBSTRATES

UNICOAT SKIMCOAT may be applied to any porous cementitious substrates which includes, one-coat base coat, 3-coat base coat, masonry, cinder block and concrete surfaces as well as old cement stucco finishes that have not been painted.

MIXING AND APPLICATION

UNICOAT SKIMCOAT should be mixed with approx 2-1/4 gallons of clean water into mixer. Add one 50 lb bag of the **UNICOAT SKIMCOAT**. Let mix for several minutes and add water as needed for desired working consistency. Mix for 4-5 minutes with a Mixing Drill and Cement Mixing Blade.

Let sit for 2 to 3 minutes, then re-mix for another 1 to 2 minutes, Skimcoat should be ready to apply.

Apply **UNICOAT SKIMCOAT SMOOTH** at approximately 1.4" maximum thickness over the recommended surfaces using a steel plaster trowel to achieve a slick smooth finish.

UNICOAT SKIMCOAT COARSE can be applied in various patterns and textures up to 1/2" maximum thickness using a steel plaster trowel.

CURING AND COVERAGES

Proper moist curing of **UNICOAT SKIMCOAT** of at least 48 hours is required for texture to harden properly. Finish Coats should not be applied for at least 7-12 days after Skimcoat application.

The addition of 1 quart of **UNICOAT ADMIXTURE 2000** to replace 1 quart of water per bag of Skimcoat Texture mix will speed the curing process up to 48 hours for application of Finish Coat.

UNICOAT SKIMCOAT covers approximately 60-100 sq ft of wall space depending on the substrate and the type of texture being applied. The thicker the texture, the less the coverage.

LIMITATIONS AND MANUFACTURER'S WARRANTY

Follow recommendations by finish manufacturers for proper applications. Proper curing is very important to the overall integrity of the system.

UNICOAT SKIMCOAT can be warranted for up to 10 years when applied by a certified applicator and all pertinent code requirements are fulfilled.

The sole warranty is replacement of materials used to correct subject material. No other warranties are either expressed or implied.



PROJECT INFORMATION

NAME:
ADDRESS:

CONTRACTOR INFORMATION

NAME:
ADDRESS:
PHONE:

ARCHITECT INFORMATION

NAME
ADDRESS
CONTACT
PHONE

DISTRIBUTOR

NAME
ADDRESS